

KAWASAKI STEEL GIHO

Vol.17 (1985) No.1

250t

(PM-Process)

Performance of Ladle Refining of BOF Melt by a 250 t Pulsating Mixing Process

(Norio Sumita)

(Yukio Oguchi)

Performance of Ladle Refining of BOF Melt by a 250 t Pulsating Mixing Process

Norio Sumita, Yukio Oguchi, Tetsuya Fujii, Toshihiko Emi, Arata Ueda, Takuro Imai

要旨

噴流式攪拌による取鍋精錬法 (PM process) の 250



Synopsis:

Mass production test for the 250-t PM process was carried out on the commercial production line and the following results were

ーを溶鋼攪拌に利用する。



3 PM 法の構造と機能の概要



金特性を把握した結果^{1~3)}に基づき、250t 溶鋼を対象とした実設備を建設した。設備の構成を Fig. 3 と Table 1 に示す。本設備は水自製鉄筋部第一制鋼工場にて、主に溶接構造由来の問題




他の代表的な精錬装置の一混合時間の測定例との比較を


100





OPEN SOURCE DOCUMENTATION / DOCUMENTATION DE DOCUMENTATION





も $0.2 \text{ mg}/10 \text{ kg}\cdot\text{steel}$ であり、RH処理材とほぼ同等である。以上よりPM法における大型介在物低減効果はRH法と同等であることがわかる。

5.3 製品の品質

PM処理の製品の品質向上効果について、低炭素Alキルド

Table 6 Quality (defect index) of products

Process	PM	RH	Ar-bubbling
Slivers of Al-killed cold sheet	0.8	—	1
Inner defects of ERW pipe (UST)	0.7	1	—

-Siキルド鋼の熱延鋼板から製造されたERWパイプの超音波探傷(UST)不良率を調査した。この結果をTable 6に示す。

処理材とRH処理材を併記した。

-
- 4) T. Fujii, U. Oguchi, N. Sumida, T. Emi and M. Saigusa :
Proc. 2nd Int. Conference on Clean Steel, The Metals
Society, Buntingford (U.K.) June 1991, 101
- 6) N. Sumida, Y. Oguchi, T. Fujii, T. Fujimura and A. Ueda :
The 2nd Japan-China Symposium on Science and
Technology of Iron and Steel, ISIJ, May 1992, 625