KAWASAKI STEEL GIHO Vol.29 (1997) No.3

A Mechanism of the Secondary Recrystallization in Grain Oriented Electrical Steel

Yasuyuki Hayakawa

Synopsis :

A mechanism of Goss texture development during the secondary recrystallization in grain oriented electrical steel is proposed based on the physical properties of the high-energy boundaries. From the analysis of the primary re crystallized texture, the frequency of the high- energy boundaries is proved to be the highest around the Goss grain. The high- energy boundary has more structural defects, which are linked to a high mobility and a high grain boundary diffusion rate. Quicker coarsening of precipitates enables high-energy boundaries to move earlier than other boundaries during final annealing. Thus, the Goss grain has a growth advantage of having the highest number of mobile boundaries during the progress of final annealing. I n order to verify the proposed model of secondary recrystallization, Monte -Carlo simulation and the investigation of the grain boundary character distribution were performed, and both simulated and experimental results supported the assumption which is use d in(p)8.8 (3[(dm 287m6Dr

方向性電磁鋼板の二次再結晶機構に関する一考察* 川崎製鉄技報 29 (1997) 3, 147-152

A Mechanism of the Secondary Recrystallization		
in Antip Quiantad Elastrical Staal		

<u><</u>	
	新ビ
	要旨
	S. A. Maria S. M. Harrison and the state of
<u>2</u> 2	
۱ <u>. </u>	
γ γ==	
-	
_	
ر <u></u>	
[<u></u>	

148 _

.- -____ **.**

_

· _		
ŕ		
, <u> </u>		
•		
· _		
	の方位に比べて多く持ち、対応粒界は一般粒界に比べて粒界易動度 0丁	
	が大きいという仮定のもとに、ゴス方位粒が、対応粒界の移動によ	
	り優先成長するという説である5.7。この説は、主として高磁東密 30 2	$30 \frac{2}{3} \frac{101}{3} 1$
· · · · · · · · · · · · · · · · · · ·	terter de la constante de la const	
·		
<u> </u>		
` <i>k</i>		
· · · · · · · · · · · · · · · · · · ·		
! *_ 		
.	<u>۴</u>	
•		
÷		
` <u> </u>	•	
` <u> </u>	•	
` <u> </u>	•	
`		
, ⁻	• • • • • • • • • • • • • • • • • • • •	
, ⁻		
, ⁻		
, ⁻		

	a ¹ ² 1	1111-1-7 15分	340.
T			
· · · · · · · · · · · · · · · · · · ·			
-			
<u></u>			
-			
	<u></u>		
		Table 2 Physical properties of grain boundaries	
in an			
17 L			
		{	
<u>.</u>			
μ _μ			
is			
₩₩			
	· -		
-			






Fig. 7 The superposition of the ODF and the value of GA_{max} (S) for various orientations (S) in Euler space ($\phi_2 = 45^{\circ}$ cross-section); (a) high permeability steel; (b) conventional steel

(a)

(b)

る方法である。各サイトに関して、ある状態からある状態への遷移 確率を各サイトのエネルギー変化量から計算して、その確率で状態 変化を起こすことが基本である。サイトはランダムに選択されて、 そのつど遷移確率を計算して状態変化を起こす。サイトの数と同じ 選択回数を1 Monte-Carlo step (MCS) と呼び、実際の時間に比例す るものと考えられている。Monte-Carlo モデルは粒成長に用いられ て、正常粒成長の解析を中心に解析的な粒成長理論の検証に使用さ

15	\mathbf{s}^2
----	----------------

	<u>¬</u> ₽ _₹	
<u>43-</u> U.s.		
	200	
)遅かった。インヒビターの抑制力が過剰な場合に Goss 方位か
		きく ND 回転した二次再結晶粒が発生することは実験的に知ら
	8 <u></u>	すめm であき面がなす好田にも き つつへんdistesting
¥.		
)		
T	1	
•		
, -		
. 9		
·		
j		
. د		
· · · -		
· 1		
	Je.	
1		
ι.		
·		
د[
1		
·		
1		
. <u> </u>		
۶. – – – – – – – – – – – – – – – – – – –		
· · · · · · · · · · · · · · · · · · ·		
~	-	
e	•	
	y	
·		
, P		
••		
1		
· · · •		
·		
·		
		
-		
·		
·		
۱ ^{··} . • • • • • • • • • • • • • • • • • • •		
8		
1		
7 		
	· · · · · · · · · · · · · · · · · · ·	
, 		
· · · · · · · · · · · · · · · · · · ·		